CBL2.2-12

12V 2.2AH

General Purpose Sealed Lead Acid Battery



CBL2.2-12




Physical Specification

Part Number:	CBL2.2-12
Length:	70.5 ± 2 mm (2.78 inches)
Width:	47.5 ± 2 mm (1.87 inches)
Container Height:	97 ± 2 mm (3.82 inches)
Total Height (with terminal):	103 ± 2 mm (4.05 inches)
Approx Weight:	0.80 Kg (1.76 lbs)

Specifications

	Nominal Voltage	12V							
	(C20 ,1.75V/cell)	2.2AH							
Terminal Option	T1								
Container Material	Standard Option	ABS							
	Flame Retardant Option (FR)	ABS (UL94:VO)							
Rated Capacity	(20hr,0.110A,1.75V/cell)	2.20 Ah							
	(10hr,0.205A,1.75V/cell)	2.05 Ah							
	(5hr,0.370A,1.75V/cell)	1.85 Ah							
	(3hr,0.538A,1.75V/cell)	1.61 Ah							
	(1hr,1.34A,1.60V/cell)	1.34 Ah							
Max Discharge Current (5s)	33A								
Internal Resistance	Approx. 95mΩ								
Discharge Characteristics		Discharge: -15°C~50°C (5°F~122°F)							
	Operating Temp. Range	Charge: -20~40°C (-4~104°F)							
		Storage: -15°C~40°C (5°F~104°F)							
	Nominal Operating Temp. Range	25 ± 3°C (77 ± 5°F)							
	Cycle Use	Initial Charging Current less than 0.66A. Voltage 14.4V~15.0V at 25°C (77°F) Temp. Coefficient -30mV/°C							
	Self Discharge	Initial Charging Current less than 0.66A. Voltage 13.5V~13.8V at 25°C (77°F) Temp. Coefficient -20mV/°C							
		40°C (104°F) 103%							
	Capacity affected by Temperature	25°C (77°F) 100%							
		0°C (32°F) 86%							
Design Floating Life at 20°C	20+ Years								
Self Discharge	Canbat Lead Acid AGM batteries may be stored for up to 6 months at 25°C (77°F) and then a refresh charge is required. For higher temperatures the time interval will be shorter. Self-discharge is less than 2 ⁶								

Dimensions




To ensure safe and efficient operation always refer to the latest edition of our datasheets, as published on our website www.canbat.com. Canbat Technologies Inc. All rights reserved. All trademarks are the property of their respective owners. All data subject to change without notice. E&O.E




Constant Current Discharge (Amperes) at 25 °C (77°F)																
F.V/Time	5min	10min	15min	20min	30min	45min	1h	1.5h	2h	3h	4h	5h	6h	8h	10h	20h
1.85V/cell	6.20	4.00	3.12	2.61	1.98	1.49	1.21	0.871	0.683	0.521	0.429	0.360	0.311	0.247	0.200	0.108
1.80V/cell	6.67	4.24	3.27	2.72	2.05	1.53	1.24	0.889	0.696	0.530	0.435	0.365	0.316	0.250	0.203	0.109
1.75V/cell	7.03	4.41	3.38	2.79	2.10	1.56	1.27	0.906	0.708	0.538	0.441	0.370	0.320	0.253	0.205	0.110
1.70V/cell	7.36	4.58	3.49	2.87	2.15	1.59	1.29	0.921	0.719	0.546	0.447	0.375	0.324	0.256	0.207	0.111
1.67V/cell	7.62	4.71	3.58	2.93	2.19	1.62	1.31	0.933	0.727	0.551	0.451	0.378	0.327	0.258	0.209	0.112
1.60V/cell	8.08	4.91	3.70	3.02	2.25	1.66	1.34	0.953	0.742	0.561	0.459	0.384	0.331	0.261	0.211	0.113

Constant Power Discharge (Watts/cell) at 25 °C (77°F)																
F.V/Time	5min	10min	15min	20min	30min	45min	1h	1.5h	2h	3h	4h	5h	6h	8h	10h	20h
1.85V/cell	11.7	7.60	5.97	5.03	3.84	2.88	2.36	1.70	1.34	1.02	0.845	0.711	0.616	0.489	0.398	0.215
1.80V/cell	12.5	8.00	6.22	5.21	3.94	2.95	2.41	1.73	1.36	1.04	0.856	0.720	0.625	0.496	0.403	0.218
1.75V/cell	13.0	8.27	6.39	5.32	4.02	3.00	2.45	1.76	1.38	1.05	0.866	0.729	0.631	0.501	0.407	0.220
1.70V/cell	13.5	8.54	6.56	5.45	4.11	3.06	2.49	1.78	1.40	1.07	0.876	0.737	0.638	0.505	0.411	0.222
1.67V/cell	13.9	8.73	6.71	5.55	4.17	3.10	2.52	1.80	1.41	1.08	0.884	0.743	0.643	0.509	0.413	0.224
1.60V/cell	14.4	8.99	6.89	5.68	4.26	3.16	2.56	1.83	1.43	1.09	0.897	0.753	0.651	0.516	0.418	0.226




Valve-Regulated Sealed Lead Acid Batteries

Sealed lead acid batteries are engineered to provide reliable power in a compact design. They are spill-proof and require zero maintenance, as adding water is never necessary. The acid in the battery is suspended in a glass mat separator, which makes the cells leak-proof during normal battery operation. Our batteries are proudly designed in Canada with quality and performance in mind, offering one of the highest cycle life among other sealed lead acid battery brands. Canbat AGM batteries are manufactured with pure lead to ensure a low self-discharge rate of less than 2%, meaning stored batteries are only required a recharge once every six months. The series also features an outer container made from ABS material.




To ensure safe and efficient operation always refer to the latest edition of our datasheets, as published on our website www.canbat.com. Canbat Technologies Inc. All rights reserved. All trademarks are the property of their respective owners. All data subject to change without notice. E&O.E


Float Charging Characteristics



Charging Voltage

Cycle Life Relation o Depth of Discharge





www.canbat.com