CBL200-6

6V 200AH

General Purpose Sealed Lead Acid Battery



CBL200-6




Physical Specification

Part Number:	CBL200-6
Length:	322 ± 2 mm (12.05inches)
Width:	178 ± 2 mm (7.01 inches)
Container Height:	226±2mm(8.90 inches)
Total Height (with terminal):	232 ± 2 mm (9.13 inches)
Approx Weight:	30.3 Kg (66.8 lbs)

Specifications

	Nominal Voltage	6V							
	(C20 ,1.75V/cell)	200AH							
Terminal Option	M8								
Container Material	Standard Option	ABS							
	Flame Retardant Option (FR)	ABS (UL94:VO)							
Rated Capacity	C20(10.4A,1.80V/cell)	208.0Ah							
	C10(20.0A,1.80V/cell)	200.0Ah							
	C5(34.4A,1.75V/cell)	172.0Ah							
	C3(52.0A,1.75V/cell)	156.0Ah							
	C1(122.0A,1.60V/cell)	122.0Ah							
Max Discharge Current (5s)	2000A								
Internal Resistance	Approx. 1.5mΩ								
Discharge Characteristics		Discharge: -15°C~50°C (5°F~122°F)							
	Operating Temp. Range	Charge: -20~40°C (-4~104°F)							
		Storage: -15°C~40°C (5°F~104°F)							
	Nominal Operating Temp. Range	25 ± 3°C (77 ± 5°F)							
	Cycle Use	Initial Charging Current less than 60.0A. Voltage 7.2V~7.5V at 25°C (77°F) Temp. Coefficient -15mV/°C							
	Self Discharge	Initial Charging Current less than 60.0A. Voltage 6.75V~6.9V at 25°C (77°F) Temp. Coefficient -10mV/°C							
		40°C (104°F) 103%							
	Capacity affected by Temperature	25°C (77°F) 100%							
	O r	0°C (32°F) 86%							
Design Floating Life at 20°C	20+ Years								
Self Discharge	Canbat Lead Acid AGM batteries may be stored for up to 6 months at 25°C (77°F) and then a refre charge is required. For higher temperatures the time interval will be shorter. Self-discharge is less than								

Dimensions




To ensure safe and efficient operation always refer to the latest edition of our datasheets, as published on our website www.canbat.com. Canbat Technologies Inc. All rights reserved. All trademarks are the property of their respective owners. All data subject to change without notice. E&O.E

CBL200-6 6V 200AH General Purpose Sealed Lead Acid Battery




Constant Current Discharge (Amperes) at 25 °C (77°F)																
F.V/Time	5min	10min	15min	20min	30min	45min	1h	1.5h	2h	3h	4h	5h	6h	8h	10h	20h
1.85V/cell	342.3	269.1	228.8	191.5	152.1	115.2	94.3	70.5	60.0	47.5	38.8	31.3	27.2	22.1	18.9	10.31
1.80V/cell	459.5	343.9	276.5	226.3	179.5	133.9	105.6	78.1	65.6	51.1	41.5	33.6	29.2	23.5	20.0	10.40
1.75V/cell	518.0	377.9	302.0	243.5	186.4	138.9	110.5	81.4	68.0	52.0	42.4	34.4	30.0	23.9	20.1	10.51
1.70V/cell	570.5	411.9	322.4	255.9	194.0	144.5	114.0	83.7	70.7	53.5	43.5	35.3	30.7	24.1	20.4	10.71
1.67V/cell	629.1	444.4	342.9	271.7	204.7	148.1	117.9	86.4	72.7	55.7	44.9	36.3	31.3	24.5	20.8	10.8
1.60V/cell	/	482.5	366.7	289.5	216.0	154.4	122.0	89.0	75.1	57.5	46.4	37.5	32.0	24.8	21.1	10.9

			(Const	ant P	ower	Discl	narge	(Wat	ts/cel	l) at 2	5 °C (77°F)			
F.V/Time	5min	10min	15min	20min	30min	45min	1h	1.5h	2h	3h	4h	5h	6h	8h	10h	20h
1.85V/cell	625.9	497.1	427.1	360.8	290.0	221.3	181.9	136.0	116.7	92.5	75.9	61.3	53.5	43.6	37.3	20.4
1.80V/cell	831.2	627.7	509.1	420.3	336.9	255.5	202.7	149.8	126.4	99.1	80.5	65.5	57.2	46.1	39.5	20.5
1.75V/cell	917.2	678.7	549.2	447.7	346.9	262.5	211.1	155.5	130.7	100.5	82.0	67.1	58.5	46.8	39.9	20.8
1.70V/cell	982.0	722.9	578.1	467.1	359.1	272.0	216.9	159.4	135.6	103.1	84.0	68.5	59.7	47.5	40.3	21.1
1.67V/cell	1067.5	773.1	610.0	492.4	375.7	276.3	222.7	163.1	138.5	106.9	86.7	70.3	60.8	48.1	40.9	21.3
1.60V/cell	1	820.1	641.6	518.9	393.9	286.4	229.3	167.4	142.5	109.7	89.1	72.3	62.0	48.4	41.3	21.5




Valve-Regulated Sealed Lead Acid Batteries


Sealed lead acid batteries are engineered to provide reliable power in a compact design. They are spill-proof and require zero maintenance, as adding water is never necessary. The acid in the battery is suspended in a glass mat separator, which makes the cells leak-proof during normal battery operation. Our batteries are proudly designed in Canada with quality and performance in mind, offering one of the highest cycle life among other sealed lead acid battery brands. Canbat AGM batteries are manufactured with pure lead to ensure a low self-discharge rate of less than 2%, meaning stored batteries are only required a recharge once every six months. The series also features an outer container made from ABS material.




Float Charging Characteristics



Cycle Life Relation o Depth of Discharge





To ensure safe and efficient operation always refer to the latest edition of our datasheets, as published on our website www.canbat.com. Canbat Technologies Inc. All rights reserved. All trademarks are the property of their respective owners. All data subject to change without notice. E&O.E

