CBL60-12

12V 60AH

General Purpose Sealed Lead Acid Battery



CBL60-12




Physical Specification

Part Number:	CBL60-12
Length:	259 ± 2 mm (10.20 inches)
Width:	168 ± 2 mm (6.61 inches)
Container Height:	208 ± 2 mm (8.19 inches)
Total Height (with terminal):	214 ± 2 mm (9.06 inches)
Approx Weight:	18.5 Kg (40.8 lbs)

Specifications

	Nominal Voltage	12V						
	(C10 ,1.75V/cell)	60AH						
Terminal Option	Т6							
Container Material	Standard Option	ABS						
	Flame Retardant Option (FR)	ABS (UL94:VO)						
Rated Capacity	(20hr,3.12A,1.80V/cell)	62.4 Ah						
	(10hr,6.00A,1.80V/cell)	60.0 Ah						
	(5hr,10.8A,1.75V/cell)	54.0 Ah						
	(3hr,16.4A,1.75V/cell)	49.2 Ah						
	(1hr,37.9A,1.60V/cell)	37.9Ah						
Max Discharge Current (5s)	600A							
Internal Resistance	Approx. 7.4mΩ							
Discharge Characteristics		Discharge: -15°C~50°C (5°F~122°F)						
	Operating Temp. Range	Charge: -20~40°C (-4~104°F)						
		Storage: -15°C~40°C (5°F~104°F)						
	Nominal Operating Temp. Range	25 ± 3°C (77 ± 5°F)						
	Cycle Use	Initial Charging Current less than 18.0A. Voltage 14.4V~15.0V at 25°C (77°F) Temp. Coefficient -30mV/°C						
	Self Discharge	Initial Charging Current less than 18.0A. Voltage 13.5V~13.8V at 25°C (77°F) Temp. Coefficient -20mV/°C						
		40°C (104°F) 103%						
	Capacity affected by Temperature	25°C (77°F) 100%						
		0°C (32°F) 86%						
Design Floating Life at 20°C	20+ Years							
Self Discharge	Canbat Lead Acid AGM batteries may be stored for up to 6 months at 25°C (77°F) and then a recharge is required. For higher temperatures the time interval will be shorter. Self-discharge is less							

Dimensions




To ensure safe and efficient operation always refer to the latest edition of our datasheets, as published on our website www.canbat.com. Canbat Technologies Inc. All rights reserved. All trademarks are the property of their respective owners. All data subject to change without notice. E&O.E

CBL60-12 12V 60AH General Purpose Sealed Lead Acid Battery




		-	(Const	ant C	urren	t Disc	harg	e (Am	peres	s) at 2	5 °C (7	77⁰F)	_	_	
F.V/Time	5min	10min	15min	20min	30min	45min	1h	1.5h	2h	3h	4h	5h	6h	8h	10h	20h
1.85V/cell	119.8	85.2	76.2	59.9	53.6	38.8	33.2	24.0	20.2	14.8	11.6	10.1	8.90	6.85	5.67	3.01
1.80V/cell	136.3	96.7	86.3	67.7	58.3	41.1	34.4	24.9	20.9	16.1	12.4	10.6	9.56	7.20	6.00	3.12
1.75V/cell	148.0	104.9	93.5	73.1	59.5	42.6	36.1	26.1	22.0	16.4	12.7	10.8	9.64	7.24	6.03	3.15
1.70V/cell	158.3	111.8	99.3	77.5	60.7	43.4	36.8	26.7	22.4	16.7	12.9	11.0	9.69	7.35	6.06	3.18
1.67V/cell	163.8	115.4	102.2	79.7	61.6	44.1	37.3	27.1	22.7	16.9	13.1	11.2	9.73	7.45	6.14	3.22
1.60V/cell	169.6	119.3	105.3	81.7	62.5	44.7	37.9	27.4	23.1	17.0	13.2	11.4	9.80	7.55	6.21	3.26

			C	onst	ant P	owerl	Disch	arge	(Watt	s/cel	l) at 2	5 °C (7	77⁰F)			
F.V/Time	5min	10min	15min	20min	30min	45min	1h	1.5h	2h	3h	4h	5h	6h	8h	10h	20h
1.85V/cell	223.8	160.3	149.4	118.0	106.0	74.6	66.5	48.3	40.7	30.0	23.6	20.6	17.6	14.1	11.7	6.20
1.80V/cell	250.4	179.3	167.1	132.0	114.5	78.5	68.5	49.7	41.8	32.4	25.1	21.6	18.8	14.8	12.2	6.42
1.75V/cell	267.2	191.4	178.3	140.9	115.9	80.8	71.5	52.0	43.9	33.0	25.5	21.9	18.9	14.8	12.3	6.48
1.70V/cell	280.9	201.2	187.5	148.1	117.3	81.9	72.6	52.8	44.6	33.5	25.9	22.2	19.0	15.0	12.4	6.54
1.67V/cell	285.5	204.5	190.5	150.5	118.1	82.6	73.2	53.3	45.0	33.6	26.2	22.5	19.0	15.2	12.6	6.61
1.60V/cell	289.5	207.3	193.2	152.6	118.6	83.0	73.8	53.7	45.4	33.8	26.4	22.8	19.1	15.3	12.7	6.68




Valve-Regulated Sealed Lead Acid Batteries


Sealed lead acid batteries are engineered to provide reliable power in a compact design. They are spill-proof and require zero maintenance, as adding water is never necessary. The acid in the battery is suspended in a glass mat separator, which makes the cells leak-proof during normal battery operation. Our batteries are proudly designed in Canada with quality and performance in mind, offering one of the highest cycle life among other sealed lead acid battery brands. Canbat AGM batteries are manufactured with pure lead to ensure a low self-discharge rate of less than 2%, meaning stored batteries are only required a recharge once every six months. The series also features an outer container made from ABS material.




Float Charging Characteristics



Cycle Life Relation o Depth of Discharge





To ensure safe and efficient operation always refer to the latest edition of our datasheets, as published on our website www.canbat.com. Canbat Technologies Inc. All rights reserved. All trademarks are the property of their respective owners. All data subject to change without notice. E&O.E