

CBL8-12



Physical Specification

Part Number: CBL8-12

Length: $151 \pm 2 \text{ mm} (5.95 \text{ inches})$


Width: $65 \pm 2 \, \text{mm} \, (2.56 \, \text{inches})$

Container Height: 93.5 ± 2 mm (3.68 inches)

Total Height (with terminal): 99.5 ± 2 mm (3.92 inches)

Approx Weight: 2.40 Kg (5.29 lbs)

	Nominal Voltage	12V							
	(C20 ,1.75V/cell)	8.0AH							
Terminal Option	T1/T2								
Container Material	Standard Option	ABS							
	Flame Retardant Option (FR)	ABS (UL94:VO)							
Rated Capacity	(20hr,0.400A,1.75V/cell)	8.00 Ah							
	(10hr,0.757A,1.75V/cell)	7.57 Ah							
	(5hr,1.40A,1.75V/cell)	7.00 Ah							
	(3hr,2.18A,1.75V/cell)	6.54 Ah							
	(1hr,5.95A,1.60V/cell)	5.95 Ah							
Max Discharge Current (5s)	120A								
Internal Resistance	Approx. 20mΩ								
Discharge Characteristics		Discharge: -15°C~50°C (5°F~122°F)							
	Operating Temp. Range	Charge: 0°C~40°C (32°F~104°F)							
		Storage: -15°C~40°C (5°F~104°F)							
	Nominal Operating Temp. Range	25 ± 3°C (77 ± 5°F)							
	Cycle Use	Initial Charging Current less than 2.40A. Voltage 14.4V~15.0V at 25°C (77°F) Temp. Coefficient -30mV/°C							
	Self Discharge	Initial Charging Current less than 2.40A. Voltage 13.5V~13.8V at 25°C (77°F) Temp. Coefficient -20mV/°C							
		40°C (104°F) 103%							
	Capacity affected by Temperature	25°C (77°F) 100%							
		0°C (32°F) 86%							
Design Floating Life at 20°C	20+ Years								
Self Discharge	Canbat Lead Acid AGM batteries may be stored for up to 6 months at 25°C (77°F) and then a refres charge is required. For higher temperatures the time interval will be shorter. Self-discharge is less than 2								





To ensure safe and efficient operation always refer to the latest edition of our datasheets, as published on our website www.canbat.com. Canbat Technologies Inc. All rights reserved. All trademarks are the property of their respective owners. All data subject to change without notice. E&O.E



Constant Current Discharge (Amperes) at 25 °C (77°F)																
F.V/Time	5min	10min	15min	20min	30min	45min	1h	1.5h	2h	3h	4h	5h	6h	8h	10h	20h
1.85V/cell	29.4	20.2	15.4	12.5	9.19	6.64	5.38	3.88	2.99	2.11	1.64	1.37	1.15	0.904	0.739	0.391
1.80V/cell	31.6	21.4	16.2	13.0	9.47	6.82	5.51	3.96	3.05	2.15	1.67	1.39	1.17	0.917	0.749	0.396
1.75V/cell	33.3	22.2	16.7	13.3	9.72	6.97	5.63	4.03	3.11	2.18	1.69	1.40	1.18	0.927	0.757	0.400
1.70V/cell	34.9	23.1	17.3	13.7	10.0	7.13	5.73	4.10	3.15	2.21	1.71	1.42	1.19	0.937	0.764	0.403
1.67V/cell	36.1	23.8	17.7	14.0	10.1	7.24	5.82	4.15	3.19	2.23	1.73	1.43	1.20	0.944	0.770	0.406
1.60V/cell	38.3	24.8	18.3	14.4	10.4	7.42	5.95	4.24	3.25	2.28	1.76	1.46	1.22	0.957	0.780	0.411

Constant Power Discharge (Watts/cell) at 25 °C (77°F)																
F.V/Time	5min	10min	15min	20min	30min	45min	1h	1.5h	2h	3h	4h	5h	6h	8h	10h	20h
1.85V/cell	55.7	38.4	29.5	24.0	17.8	12.9	10.5	7.57	5.86	4.15	3.24	2.70	2.27	1.79	1.47	0.782
1.80V/cell	59.3	40.4	30.8	24.9	18.2	13.2	10.7	7.71	5.96	4.21	3.28	2.73	2.30	1.82	1.49	0.791
1.75V/cell	61.8	41.7	31.6	25.4	18.6	13.4	10.9	7.82	6.05	4.27	3.32	2.76	2.33	1.84	1.50	0.800
1.70V/cell	64.1	43.1	32.5	26.0	19.0	13.7	11.0	7.94	6.12	4.32	3.36	2.80	2.35	1.85	1.52	0.807
1.67V/cell	65.7	44.1	33.2	26.5	19.3	13.9	11.2	8.02	6.18	4.36	3.39	2.82	2.37	1.87	1.53	0.813
1.60V/cell	68.4	45.4	34.1	27.2	19.7	14.1	11.4	8.16	6.28	4.43	3.44	2.85	2.40	1.89	1.54	0.822








Float Charging Characteristics

Valve-Regulated Sealed Lead Acid Batteries

Sealed lead acid batteries are engineered to provide reliable power in a compact design. They are spill-proof and require zero maintenance, as adding water is never necessary. The acid in the battery is suspended in a glass mat separator, which makes the cells leak-proof during normal battery operation. Our batteries are proudly designed in Canada with quality and performance in mind, offering one of the highest cycle life among other sealed lead acid battery brands. Canbat AGM batteries are manufactured with pure lead to ensure a low self-discharge rate of less than 2%, meaning stored batteries are only required a recharge once every six months. The series also features an outer container made from ABS material.







To ensure safe and efficient operation always refer to the latest edition of our datasheets, as published on our website www.canbat.com. Canbat Technologies Inc. All rights reserved. All trademarks are the property of their respective owners. All data subject to change without notice. E&O.E