

CHT400-2

2V 400AH

High Temperature Battery

CANBAT

CHT400-2



Physical Specification





Part Number:	CHT400-2
Length:	210 ± 2 mm (8.26 inches)
Width:	175 ± 2 mm (6.89 inches)
Container Height:	330 ± 2 mm (12.99 inches)
Total Height (with terminal):	350 ± 2 mm (13.78 inches)
Approx Weight:	29.2 kg (64.38 lbs)

Specifications

	Nominal Voltage	2V
	Nominal Capacity (10HR)	400AH
Terminal Options	Standard Terminal	T11
	Terminal Specs	(M8,Torque11~14.7N m)
Container Material	Standard Option	ABS (High Temperature Resistant Material)
	Flame Retardant Option (FR)	ABS (UL94:VO)
Rated Capacity(35°)	C20(21.2A,1.80V/cell)	424.0 Ah
	C10(40.0A,1.80V/cell)	400.0 Ah
	C5(71.0A,1.75V/cell)	355.0Ah
	C3(106.0A,1.75V/cell)	318.0 Ah
	C1(246.0A,1.67V/cell)	246.0 Ah
Max Discharge Current	2400A (5s)	
Internal Resistance	Approx 0.6mΩ	
Discharge Characteristics	Operating Temp. Range	The battery can operate at temperatures of -40C ~ +65C. Extreme temperature can be up to 80C.
	Nominal Operating Temp. Range	25 ± 3°C (77 ± 5°F)
	Cycle Use	Initial Charging Current less than 100A.Voltage 2.35V ~ 2.40V at 25°C (77°F) Temp. Coefficient -30mV/°C
	Standby Use	Initial Charging Current less than 100A.Voltage 2.25V at 25°C (77°F) Temp. Coefficient -20mV/°C
	Capacity affected by Temperature	40°C (104°F) 103%
		25°C (77°F) 100%
		0°C (32°F) 79%
Design Floating Life at 20°C	5 Years	
Self Discharge	Canbat High Temperature Batteries may be stored for up to 6 months at 25°C(77F) and then a refresh charge is required. For higher temperatures the time interval will be shorter.	

Dimensions

T11 Terminal



To ensure safe and efficient operation always refer to the latest edition of our datasheets, as published on our website www.canbat.com. Canbat Technologies Inc. All rights reserved. All trademarks are the property of their respective owners. All data subject to change without notice. E&O.E


Constant Current Discharge (Amperes) at 35° C (95° F)

F.V/Time	5min	10min	15min	20min	30min	45min	1h	2h	3h	4h	5h	6h	8h	10h	20h
1.85V/cell	466.7	396.0	361.4	325.2	273.6	224.0	188.4	124.8	96.2	77.7	65.5	57.1	45.6	38.2	20.2
1.80V/cell	568.0	463.2	411.9	366.0	301.6	243.2	204.2	133.2	101.1	81.0	68.2	59.2	47.5	40.0	21.2
1.75V/cell	663.9	532.8	466.0	410.4	330.4	265.1	223.0	140.8	106.0	85.0	71.0	61.4	48.8	40.8	21.6
1.70V/cell	759.7	597.6	515.0	446.4	355.2	281.1	236.0	147.8	110.7	88.0	73.2	63.3	50.3	41.8	22.2
1.67V/cell	815.6	643.2	555.2	480.0	376.0	293.3	246.0	153.6	114.2	90.5	75.2	64.8	50.9	42.5	22.5
1.60V/cell	888.0	688.8	588.8	504.0	392.8	306.1	256.4	159.4	116.9	92.5	76.7	66.0	51.8	42.9	22.7


Constant Power Discharge (Watts/cell) at 35 °C (95° F)

F.V/Time	5min	10min	15min	20min	30min	45min	1h	2h	3h	4h	5h	6h	8h	10h	20h
1.85V/cell	871.6	745.0	684.3	618.5	522.9	430.7	364.4	242.7	188.1	152.4	129.1	112.9	90.5	76.1	40.3
1.80V/cell	1043.4	858.8	769.8	688.8	571.7	464.5	392.8	257.8	196.6	158.3	133.8	116.5	94.0	79.4	42.1
1.75V/cell	1198.3	972.1	858.6	763.5	621.6	503.3	427.1	271.5	205.6	165.6	138.9	120.5	96.3	80.9	42.9
1.70V/cell	1348.5	1075.1	939.3	823.4	662.6	530.0	449.5	283.8	213.9	170.7	142.6	124.1	99.1	82.9	44.0
1.67V/cell	1421.7	1139.9	999.9	875.9	696.2	550.0	465.9	293.7	219.7	175.0	146.0	126.6	100.1	84.1	44.6
1.60V/cell	1515.8	1196.8	1042.9	909.2	720.0	568.6	482.4	302.9	223.7	178.1	148.4	128.5	101.7	84.7	44.9


Discharge Characteristics




Float Charging Characteristics




Temperature Effects in Relation to Battery Capacity




Effect of Temperature on Long Term Float Life



Cycle Life in Relation to Depth of Discharge



Self Discharge Characteristics



- A** No supplementary required
(Carryout supplementary charge before use if 100% capacity is required.)
- B** Supplementary charge required before use. Optional charging way as below:
1. Charged for above 3 days at limited current 0.25CA and constant voltage 2.25V/cell.
2. Charged for above 20 hours at limited current 0.25CA and constant voltage 2.25V/cell.
3. Charged for 8 ~ 10 hours at limited current 0.05 CA.
- C** Supplementary charge may often fail to recover the capacity.
The battery should never be left standing till this is reached.

To ensure safe and efficient operation always refer to the latest edition of our datasheets, as published on our website www.canbat.com. Canbat Technologies Inc. All rights reserved. All trademarks are the property of their respective owners. All data subject to change without notice. E&O.E