



Physical Specification

Part Number: CLC150-12FT

Length: 559 ± 2 mm (22.01 inches)


Width: $125 \pm 2 \, \text{mm} (4.92 \, \text{inches})$

Container Height: 277 ± 2 mm (10.91 inches)

Total Height (with terminal): 277 ± 2 mm (10.91 inches)

Approx Weight: 48.0 kg (105.8 lbs)

	Nominal Voltage	12V						
	Nominal Capacity (10HR)	150AH						
Terminal Type	Standard Terminal	M8						
	Optional Terminal	M6						
Container Material	Standard Option	ABS						
	Flame Retardant Option (FR)	Non-halogenated, thermally sealed PPOI plastic casing & cove						
Rated Capacity(35°)	150Ah	(C10 to 1.80VDC @ 25°C)						
	150Ah	(C8 to 1.75VDC @ 25°C)						
	145.5Ah	(C5 to 1.75VDC @ 25°C)						
	131.7Ah	(C3 to 1.75VDC @ 25°C)						
Max Charge Current (A)	45.0A							
Max Discharge Current	1800A							
Internal Resistance	Approx 4.0mΩ @ 25°C @ 1Khz							
Discharge Characteristics	Operating Temp. Range	-40 ~ 65°C						
	Nominal Operating Temp. Range	25 ± 3°C (77 ± 5°F)						
	Cycle Life	Exceptional PSoC cyclic performance 2500+ cycles at 50% Depth of Discharge (DoD)						
	Features	Lead carbon added to negative electrodes increases power and reduces sulfation, leak-proof operation						
	Capacity affected by Temperature	40°C (104°F) 103%						
		25°C (77°F) 100%						
		0°C (32°F) 79%						
Design Floating Life at 20°C	20+ Years	•						
Self Discharge		nay be stored for up to 24 months at 25°C (°77F). For higher shorter. A refresh charge is required when the OCV approach						





To ensure safe and efficient operation always refer to the latest edition of our datasheets, as published on our website www.canbat.com. Canbat Technologies Inc. All rights reserved. All trademarks are the property of their respective owners. All data subject to change without notice. E&O.E


Pure Lead Carbon


Constant Current Discharge (Amperes) at 25 °C (77°F)													
F.V/Time	10 min	15min	20min	30min	45min	1h	2h	3h	4h	5h	8h	10h	20h
1.85V/cell	236.0	190.7	165.2	136.6	110.0	94.5	56.5	41.7	32.6	27.7	17.9	14.7	7.65
1.80V/cell	260.9	208.0	177.2	145.1	116.0	99.0	58.6	43.1	33.7	28.5	18.5	15.0	7.80
1.75V/cell	282.1	222.0	187.5	151.6	120.0	102.0	59.9	43.9	34.3	29.1	18.8	15.3	7.88
1.70V/cell	298.7	234.1	196.1	157.1	124.0	105.0	60.9	44.5	34.6	29.4	19.0	15.5	7.91
1.67V/cell	306.7	240.0	200.4	159.8	128.0	106.8	61.3	44.7	34.9	29.6	19.1	15.6	7.95
1.60V/cell	318.0	249.8	207.2	163.6	132.0	108.8	61.8	44.9	35.0	29.8	19.2	15.6	7.98

Constant Power Discharge (Watts/cell) at 25 °C (77°F)													
F.V/Time	10 min	15min	20min	30min	45min	1h	2h	3h	4h	5h	8h	10h	20h
1.85V/cell	472.9	380.6	331.0	276.7	220.2	185.2	115.3	84.7	66.3	56.2	35.9	29.7	15.8
1.80V/cell	512.4	405.9	354.3	292.9	230.2	194.7	119.4	86.5	67.5	57.3	36.4	29.8	16.1
1.75V/cell	547.7	428.2	370.7	303.7	236.5	198.1	121.6	87.9	68.5	58.1	37.0	30.8	16.3
1.70V/cell	577.7	446.6	384.2	312.3	241.0	201.3	123.2	88.8	69.3	58.7	37.4	31.1	16.6
1.67V/cell	592.5	455.5	390.8	316.4	243.6	202.2	123.9	89.2	69.6	58.9	37.6	31.3	16.7
1.60V/cell	616.9	469.8	400.8	322.4	246.4	203.3	124.7	89.7	70.0	59.3	37.8	32.0	16.8









Features of Canbat Carbon Technology

Exceptional PSoC cyclic performance 2500 cycles @50% DoD with a design life of 12+ years at 20°C (68°F)

High modulus Polyphenylene Oxide (PPO) plastic, materials designed to withstand extended elevated operating temperatures.

Flame retardant (UL 94 VO) and LOI of at least 28%

Lead carbon added to negative electrodes increases power and reduces sulfation

High potential fuel savings when used with hybrid genset applications

Operating temperature range -40°C to +65°C (-40°F to 149°F)

State-of-the-art automated manufacturing ensures consistency and reliability

Advanced 3 stage terminal design to ensure leak-free operation - brass terminals provide maximum performance

Non-halogenated thermally sealed plastic casing