



Physical Specification

Part Number: CLC170-12FT

Length: 559 ± 2 mm (22.01 inches)


Width: $125 \pm 2 \, \text{mm} (4.92 \, \text{inches})$

Container Height: 320 ± 2 mm (12.60 inches)

Total Height (with terminal): 320 ± 2 mm (12.60 inches)

Approx Weight: **54.2 kg (119.5 lbs)**

Specifications								
	Nominal Voltage	12V						
	Nominal Capacity (10HR)	170AH						
Terminal Type	Standard Terminal	M8						
	Optional Terminal	M6						
Container Material	Standard Option	ABS						
	Flame Retardant Option (FR)	Non-halogenated, thermally sealed PPOI plastic casing & cov						
Rated Capacity(35°)	170.0Ah	(C10 to 1.80VDC @ 25°C)						
	170.4Ah	(C8 to 1.75VDC @ 25°C)						
	166.5Ah	(C5 to 1.75VDC @ 25°C)						
	135.9Ah	(C3 to 1.75VDC @ 25°C)						
Max Charge Current (A)	51.0A							
Max Discharge Current	2040A							
Internal Resistance	Approx 3.2mΩ @ 25°C @ 1Khz							
Discharge Characteristics	Operating Temp. Range -40 ~ 65°C							
	Nominal Operating Temp. Range	25 ± 3°C (77 ± 5°F)						
	Cycle Life	Exceptional PSoC cyclic performance 2500+ cycles at 50% Depth of Discharge (DoD)						
	Features	Lead carbon added to negative electrodes increases power and reduces sulfation, leak-proof operation						
	Capacity affected by Temperature	40°C (104°F) 103%						
		25°C (77°F) 100%						
		0°C (32°F) 79%						
Design Floating Life at 20°C	20+ Years	•						
Self Discharge	temperatures, the time interval will be	nay be stored for up to 24 months at 25°C (°77F). For higher shorter. A refresh charge is required when the OCV approach age time is reached, whichever occurs first.						





To ensure safe and efficient operation always refer to the latest edition of our datasheets, as published on our website www.canbat.com. Canbat Technologies Inc. All rights reserved. All trademarks are the property of their respective owners. All data subject to change without notice. E&O.E





Constant Current Discharge (Amperes) at 25 °C (77°F)													
F.V/Time	10 min	15min	20min	30min	45min	1h	2h	3h	4h	5h	8h	10h	20h
1.85V/cell	246.9	212.2	185.3	144.2	110.6	98.6	57.0	42.5	35.7	31.6	20.2	16.8	8.67
1.80V/ceII	272.3	233.8	200.9	154.9	117.9	103.7	59.5	44.2	37.0	32.6	20.8	17.0	8.76
1.75V/cell	294.9	249.9	212.9	161.9	122.6	108.8	61.2	45.3	38.3	33.3	21.3	17.3	8.84
1.70V/cell	313.6	263.7	223.0	167.7	126.4	112.2	62.9	46.5	39.1	33.7	21.7	17.7	8.93
1.67V/cell	322.6	270.6	228.0	170.5	128.2	115.6	64.6	47.6	40.0	34.0	22.1	17.9	9.01
1.60V/cell	336.0	281.3	235.7	174.9	130.9	119.0	65.5	48.2	40.4	34.7	22.3	18.0	9.10

Constant Power Discharge (Watts/cell) at 25 °C (77°F)													
F.V/Time	10 min	15min	20min	30min	45min	1h	2h	3h	4h	5h	8h	10h	20h
1.85V/cell	482.6	409.8	358.4	281.3	217.3	196.4	119.6	94.7	77.0	64.1	42.8	35.0	18.8
1.80V/cell	522.9	444.9	388.4	302.6	232.6	200.6	125.7	96.8	78.9	65.7	43.9	36.1	19.3
1.75V/cell	559.0	466.1	406.6	313.2	239.6	204.7	128.7	98.0	79.8	66.5	44.5	36.2	19.6
1.70V/cell	589.6	483.4	420.7	321.4	245.0	208.5	130.6	98.9	80.4	66.9	44.6	36.3	19.7
1.67V/cell	604.7	491.5	426.5	325.1	247.6	213.4	131.2	99.1	80.6	67.1	44.8	36.4	19.7
1.60V/cell	629.7	500.5	430.7	327.4	248.4	214.2	131.6	99.2	80.9	67.3	44.9	36.6	19.8









Features of Canbat Carbon Technology

Exceptional PSoC cyclic performance 2500 cycles @50% DoD with a design life of 12+ years at 20°C (68°F)

High modulus Polyphenylene Oxide (PPO) plastic, materials designed to withstand extended elevated operating temperatures.

Flame retardant (UL 94 VO) and LOI of at least 28%

Lead carbon added to negative electrodes increases power and reduces sulfation

High potential fuel savings when used with hybrid genset applications

Operating temperature range -40°C to +65°C (-40°F to 149°F)

State-of-the-art automated manufacturing ensures consistency and reliability

Advanced 3 stage terminal design to ensure leak-free operation - brass terminals provide maximum performance

Non-halogenated thermally sealed plastic casing